

## PRINTHARMONY GLOSS

Basis weight	Gsm (g/m <sup>2</sup> )	51.0	54.0	57.0	60.0	65.0
Thickness	um (μ)	46±3	48±3	46±3	50±3	55±3
Density	g/ c 3	1.11	1.09	1.19	1.21	1.19
Oken smoothness	sec	900	900	2000	1900	1700
Oken smoothness	sec	800	800	1900	1700	1600
Gloss (75°, Hunter)	%	36.0±3.0	36.0±3.0	50.0±5.0	50.0±5.0	50.0±5.0
Gloss (75°, Hunter)	%	36.0±3.0	36.0±3.0	50.0±5.0	50.0±5.0	50.0±5.0
Brightness(C/2)	%	72.0±2.0	72.0±2.0	82.5±2.0	82.5±2.0	82.5±2.0
Opacity	%	92	93	89	92	93

## PRINTHARMONY GLOSS

Basis weight	Gsm (g/m <sup>2</sup> )	70	75	80
Thickness	um (μ)	53	57	62
Gloss Hunter	%	57	57	60
ISO Brightness	%	84	84	84
Opacity	%	88	90	92



100%



[www.unglobalcompact.org/](http://www.unglobalcompact.org/)

## Placement Dates

All products have the following Lead Times:

- A) Cycle closes 22nd each month, produced the following & then delivery late the next/early one after.  
For Example: Order 22nd July, Produced in August, delivery to store late September/ early October .  
(This applies to all products, please note A2 grades ex Akita can be an additional 1 to 2 weeks)
- B) Cycle closes 10th each month, produced later that month & delivery mid to late the following.  
For Example: Order 10th August, Produced late August, delivery approx Mid October.  
(This only applies to LWC 51 & 54gsm ex Ishinomaki N6 Machine)

## Estimated Shipping Dates